



Formosa Plastics®

Formolene® PP

Formolene 6510A

Impact Copolymer for Injection Molding

Formolene 6510A is a medium impact copolymer of polypropylene characterized by its easy mold flow, physical property balance and excellent dimensional stability. It has found use in applications including closures, housewares, small appliances, and battery cases and lids.

Formolene 6510A meets all requirements of the U. S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact.

Typical Properties of this Commercial Grade

Melt Flow Rate, I ₂ @ 230°C, g/10 min	ASTM D1238	10.0
Density, g/cm ³	ASTM D1505	0.9
Tensile Strength at Yield (50 mm/min), psi	ASTM D638	3,500
Elongation at Yield (50 mm/min), %	ASTM D638	7
Flexural Modulus (1.3 mm/min), 1% Secant, psi	ASTM D790	150,000
Rockwell Hardness, R Scale	ASTM D785	100
Notched Izod Impact Strength @ 73°F, ft-lb/in	ASTM D256	2.5

Note: Specimens were injection molded according to the conditions specified in ASTM D4101.

Published 2/01, Reviewed 01/07

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 716-7230

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.



ISO 9001:2000
FS 70459
FM 31429
FM 46020



ISO 14001
EMS 35710