

Impact - 6523WZ produces molded parts with improved impact compared with parts molded from homopolymer polypropylene.

Antistat - 6523WZ contains an antistat to help protect molded parts from dust accumulation.

FDA - 6523WZ complies with all applicable FDA regulations for food contact applications.

Recommended Applications - 6523WZ is recommended for injection molding housewares, caps and closures and other items calling for a combination of good impact, and easy mold release.

Processing - 6523WZ resin processes on conventional injection molding equipment with typical melt temperatures of 390-450°F (200-232°C). Call the nearest Total Petrochemicals Polypropylene Sales Office for additional information.

<u>Resin Properties</u> ⁽¹⁾	<u>ASTM Method</u>	<u>Typical Value</u>
Melt Flow, g/10 min.	10	D-1238 Condition "L"
Density, g/cc	0.900	D-1505
Melting Point, °F (°C)	300 (149)	DSC ⁽²⁾
Haze, 0.04" plaques, %	35	D-1003
 <u>Mechanical Properties</u>⁽¹⁾		
Tensile, psi (M Pa)	4,400 (30)	D-638
Elongation, %	9	D-638
Tensile Modulus, psi (M Pa)	190,000 (1,300)	D-638
Flexural Modulus, psi (M Pa)	170,000 (1,200)	D-790
Izod Impact @ 73°F		D-256A
Notched - ft.lb./in. (J/m)	0.8 (45)	
Unnotched - ft.lb./in. (J/m)	No Breaks	
Hardness		
Rockwell R	90	D-785A
 <u>Thermal Properties</u>⁽¹⁾		
Heat Deflection		D-648
°F @ 66 psi	182	
°C @ 4.64 kg/cm ²	83	

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.
 (2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.

6523WZ 06/11

Corporate Office USA
 P.O. Box 674411
 Houston, TX 77267-4411
 800.344.3462
www.totalpetrochemicalsusa.com

Technical Center
 P.O. Box 1200
 Deer Park, TX 77536
 281.884.7500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.